



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ariya Alpacas Inc
411 Brill Road
West Bolton QC, J0E 2T0 Canada

Date: 28-Jul-20
Shear ID:
Test No: 200871


Animal and Sample Description

Animal Name: ARIYA PURE RESERVE'S JOPHIEL
Registry #: 35484752
Breed: Huacaya
Sex: Male
Colour: 205 - Dark Fawn

Date of Birth (Age):
Sample Location: GRID
Sample Date:
Previous Shear Date:
Total Fleece Wt (lbs): 0.00

Laboratory Data

Mean Fiber Diameter:	17.6 microns	Mean Staple Length:	81 mm
Standard Deviation:	4.1 microns	Length Standard Deviation:	2.3 mm
Coefficient of Variation:	23.2 %	Length Coefficient of Variation:	2.8 %
Spin Fineness:	17.4 microns	Mean Curvature:	50.5 deg/mm
Fibers Greater Than 30 microns:	0.6 %	SD Curvature:	31.1 deg/mm
Comfort Factor:	99.4 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com