



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ariya Alpacas
411 Brill Road, West Bolton
Quebec J0E 2T0 CA

Date: 13-Apr-21
Shear ID:
Test No: 600378

Animal and Sample Description


Animal Name: Silver & Silk'S Cria (2020) DI
Registry #:
Breed:
Sex: Female
Colour: Dark Fawn

Date of Birth (Age): 16-Jul-20
Sample Location: Right Side
Sample Date: 1-Mar-21
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter: 17.1 microns
Standard Deviation: 3.4 microns
Coefficient of Variation: 19.8 %
Spin Fineness: 16.4 microns
Fibers Greater Than 30 microns: 0.5 %

Comfort Factor: 99.5 %
Mean Curvature: 51.2 deg/mm
SD Curvature: 19.6 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com