



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Janette Archambault
411 Chemin De Brill, RR32 Bolton-Quest
QC J0E 2T0, CA

Date: 16-May-22
Shear ID:
Test No: 606120


Animal and Sample Description

Animal Name: Ariya Divine Love's Providence
Registry #: 36185405
Breed: Huacaya
Sex: Female
Colour: 410 - Dark Brown

Date of Birth (Age): 2-Sep-21
Sample Location: GRID
Sample Date: 15-Apr-22
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	16.6 microns	Mean Staple Length:	97 mm
Standard Deviation:	4.3 microns	Length Standard Deviation:	9.4 mm
Coefficient of Variation:	25.7 %	Length Coefficient of Variation:	9.7 %
Spin Fineness:	16.8 microns	Mean Curvature:	51.7 deg/mm
Fibers Greater Than 30 microns:	0.9 %	SD Curvature:	21.3 deg/mm
Comfort Factor:	99.1 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com