



**Optical Fiber Diameter Analyser (OFDA100)
Micron Test Report**

Alpagas Charlevoix
2643 Route Du Fleuve Les Eboulements
G0A2M0 CA

Date: 13-Apr-21
Shear ID: 956000006324612
Test No: 600406


Animal and Sample Description

Animal Name: Kenzo De Charlevoix
Registry #: 35592914
Breed: Huacaya
Sex: Male
Colour: 205 - Dark Fawn

Date of Birth (Age): 5-Aug-19
Sample Location: SIDE
Sample Date: 1-Jun-20
Previous Shear Date: 1-Jun-19
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	15.7 microns	Comfort Factor:	99.5 %
Standard Deviation:	3.9 microns	Mean Curvature:	39.2 deg/mm
Coefficient of Variation:	25.0 %	SD Curvature:	21.3 deg/mm
Spin Fineness:	15.8 microns		
Fibers Greater Than 30 microns:	0.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com