



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Alpagas Charlevoix
2643 Route Du Fleuve Les Eboulements
G0A2M0 CA

Date: 13-Apr-21
Shear ID: 95600005594099
Test No: 600400

Animal and Sample Description


Animal Name: Tonto Teho De Charlevoix
Registry #: 35121732
Breed: Huacaya
Sex: Male
Colour: 204 - Medium Fawn

Date of Birth (Age): 22-Jul-18
Sample Location: SIDE
Sample Date: 1-Jun-20
Previous Shear Date: 1-Jun-19
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter: 17.0 microns
Standard Deviation: 3.4 microns
Coefficient of Variation: 20.2 %
Spin Fineness: 16.4 microns
Fibers Greater Than 30 microns: 0.4 %

Comfort Factor: 99.6 %
Mean Curvature: 42.4 deg/mm
SD Curvature: 20.4 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com