



**Optical Fiber Diameter Analyser (OFDA100)  
Micron Test Report**

Alpagas Charlevoix  
2643 Route Du Fleuve Les Eboulements  
G0A2M0 CA

Date: 13-Apr-21  
Shear ID: 95600007792279  
Test No: 600404


**Animal and Sample Description**

Animal Name: Arya Pure Blackout De Charlevoix  
Registry #: 35592952  
Breed: Huacaya  
Sex: Male  
Colour: 500 - True Black

Date of Birth (Age): 13-Aug-18  
Sample Location: SIDE  
Sample Date: 1-Jun-20  
Previous Shear Date: 1-Jun-19  
Total Fleece Wt (lbs):

**Laboratory Data**

Mean Fiber Diameter:	15.4 microns	Comfort Factor:	99.5 %
Standard Deviation:	3.7 microns	Mean Curvature:	34.8 deg/mm
Coefficient of Variation:	24.2 %	SD Curvature:	18.3 deg/mm
Spin Fineness:	15.4 microns		
Fibers Greater Than 30 microns:	0.5 %		



**Test Performed According to Method AS/NZS 4492.5:2000**

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below  
SGS NZ LTD - 48 Kemp Street, Kibimie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)