



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Marjorie Lamontagne
461 6E Rang, Sainte-Hedwidge
QC G8H 0B2, CA

Date: 21-Jul-23
Shear ID: 250291
Test No: 613499


Animal and Sample Description

Animal Name: Sansa du Lac
Registry #: 35533122
Breed: Huacaya
Sex: Female
Colour: 204 - Medium Fawn

Date of Birth (Age): 3-Jul-21
Sample Location: GRID
Sample Date: 21-May-23
Previous Shear Date: 21-May-22
Total Fleece Wt (lbs): 4.60

Laboratory Data

Mean Fiber Diameter:	21.0 microns	Mean Staple Length:	124 mm
Standard Deviation:	4.2 microns	Length Standard Deviation:	2.6 mm
Coefficient of Variation:	20.1 %	Length Coefficient of Variation:	2.1 %
Spin Fineness:	20.3 microns	Mean Curvature:	44.3 deg/mm
Fibers Greater Than 30 microns:	2.2 %	SD Curvature:	18.2 deg/mm
Comfort Factor:	97.8 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com