



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable  
177 Ch Poulin  
Dubswell, Marbleton QC Job 2LO, CANADA

Date: 28-Jan-21  
Shear ID:  
Test No: 600012


### Animal and Sample Description

Animal Name: Criadorable Daryl  
Registry #:  
Breed: Huacaya  
Sex: Male  
Colour: White

Date of Birth (Age): 26-Jul-19  
Sample Location: GRID  
Sample Date:  
Previous Shear Date:  
Total Fleece Wt (lbs):

### Laboratory Data

Mean Fiber Diameter:	17.8 microns	Mean Staple Length:	131 mm
Standard Deviation:	3.5 microns	Length Standard Deviation:	8.4 mm
Coefficient of Variation:	19.4 %	Length Coefficient of Variation:	6.4 %
Spin Fineness:	17.1 microns	Mean Curvature:	42.6 deg/mm
Fibers Greater Than 30 microns:	0.6 %	SD Curvature:	21.7 deg/mm
Comfort Factor:	99.4 %	Medullated Fibers:	2.4 %



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)