



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable  
177 Ch Poulin  
Dubswell, Marbleton QC Job 2LO, CANADA

Date: 28-Jan-21  
Shear ID:  
Test No: 600014


### Animal and Sample Description

Animal Name: Criadorable Renegat  
Registry #:  
Breed: Huacaya  
Sex: Male  
Colour: Bay Black

Date of Birth (Age):  
Sample Location: GRID  
Sample Date:  
Previous Shear Date:  
Total Fleece Wt (lbs):

### Laboratory Data

Mean Fiber Diameter:	24.3 microns	Mean Staple Length:	110 mm
Standard Deviation:	5.4 microns	Length Standard Deviation:	9.7 mm
Coefficient of Variation:	22.0 %	Length Coefficient of Variation:	8.8 %
Spin Fineness:	23.8 microns	Mean Curvature:	29.1 deg/mm
Fibers Greater Than 30 microns:	10.4 %	SD Curvature:	16.1 deg/mm
Comfort Factor:	89.6 %	Medullated Fibers:	%



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)