



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ferme Criadorable
177 Ch Poulin
Dubswell, Marbleton QC Job 2LO, CANADA

Date: 28-Jan-21
Shear ID:
Test No: 600007


Animal and Sample Description

Animal Name: Criadorable Mateo
Registry #:
Breed: Huacaya
Sex: Female
Colour: Black

Date of Birth (Age): 19-Jun-18
Sample Location: GRID
Sample Date:
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	21.4 microns	Mean Staple Length:	123 mm
Standard Deviation:	4.3 microns	Length Standard Deviation:	4.1 mm
Coefficient of Variation:	20.3 %	Length Coefficient of Variation:	3.3 %
Spin Fineness:	20.7 microns	Mean Curvature:	39.9 deg/mm
Fibers Greater Than 30 microns:	3.2 %	SD Curvature:	21.2 deg/mm
Comfort Factor:	96.8 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com