



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Criadorable
177 Ch Poulin, Dudswell
QC J0B 2L0, CA

Date: 19-Oct-21
Shear ID:
Test No: 605329


Animal and Sample Description

Animal Name: Criadorable Michonne
Registry #:
Breed: Huacaya
Sex: Female
Colour: 204 - Medium Fawn

Date of Birth (Age): 13-Aug-19
Sample Location: GRID
Sample Date: 25-May-21
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

| | | | |
|---------------------------------|--------------|----------------------------------|-------------|
| Mean Fiber Diameter: | 20.1 microns | Mean Staple Length: | 98 mm |
| Standard Deviation: | 3.8 microns | Length Standard Deviation: | 7.2 mm |
| Coefficient of Variation: | 18.8 % | Length Coefficient of Variation: | 7.3 % |
| Spin Fineness: | 19.2 microns | Mean Curvature: | 50.0 deg/mm |
| Fibers Greater Than 30 microns: | 1.5 % | SD Curvature: | 21.8 deg/mm |
| Comfort Factor: | 98.5 % | | |



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com