



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Criadorable
177 Ch Poulin, Dudswell
QC J0B 2L0, CA

Date: 19-Oct-21
Shear ID:
Test No: 605337


Animal and Sample Description

Animal Name: Criadorable Ricki
Registry #:
Breed: Huacaya
Sex: Male
Colour: 100 - White

Date of Birth (Age): 20-Jul-20
Sample Location: GRID
Sample Date: 25-May-21
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	17.4 microns	Mean Staple Length:	118 mm
Standard Deviation:	3.8 microns	Length Standard Deviation:	4.8 mm
Coefficient of Variation:	21.9 %	Length Coefficient of Variation:	4.0 %
Spin Fineness:	17.0 microns	Mean Curvature:	48.9 deg/mm
Fibers Greater Than 30 microns:	0.6 %	SD Curvature:	21.8 deg/mm
Comfort Factor:	99.4 %	Medullated Fibers:	1.1 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com