



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Ariya Alpacas
411 Brill Road, West Bolton
Quebec J0E 2T0 CA

Date: 13-Apr-21
Shear ID:
Test No: 600353


Animal and Sample Description

Animal Name: Ebony'S Cria (2020)
Registry #:
Breed:
Sex: Female
Colour: Dark Brown

Date of Birth (Age): 24-Jul-20
Sample Location: Right Side
Sample Date: 1-Mar-21
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	16.1 microns	Comfort Factor:	99.5 %
Standard Deviation:	3.2 microns	Mean Curvature:	51.8 deg/mm
Coefficient of Variation:	19.6 %	SD Curvature:	19.0 deg/mm
Spin Fineness:	15.5 microns		
Fibers Greater Than 30 microns:	0.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com