



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Enchanted Farms  
31620 NE 129th St, Duvall  
WA 98019-7244, US

Date: 16-Oct-23  
Shear ID: 256448  
Test No: 614847


### Animal and Sample Description

Animal Name: SUNNY ACCOYO ADMIRAL  
Registry #: 35055549  
Breed: Huacaya  
Sex: Male  
Colour: 100 - White

Date of Birth (Age): 30-Oct-14  
Sample Location: GRID  
Sample Date: 7-May-23  
Previous Shear Date: 12-May-22  
Total Fleece Wt (lbs):

### Laboratory Data

Mean Fiber Diameter:	26.9 microns	Mean Staple Length:	84 mm
Standard Deviation:	6.3 microns	Length Standard Deviation:	7.3 mm
Coefficient of Variation:	23.2 %	Length Coefficient of Variation:	8.7 %
Spin Fineness:	26.7 microns	Mean Curvature:	44.4 deg/mm
Fibers Greater Than 30 microns:	19.4 %	SD Curvature:	23.5 deg/mm
Comfort Factor:	80.6 %	Medullated Fibers:	23.9 %



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Ioasa Kosena  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [WoolOnline@sgs.com](mailto:WoolOnline@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)