



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Dave Wiegman
PO BOX 1683, Flagstaff
AZ 86002-1683 US

Date: 19-Oct-22
Shear ID: 235955
Test No: 609062

Animal and Sample Description


Animal Name: Ccap A Shot Of Rumm
Registry #: 35137702
Breed: Huacaya
Sex: Male
Colour: 205 - Dark Fawn

Date of Birth (Age): 26-Aug-16
Sample Location: GRID
Sample Date: 15-Apr-22
Previous Shear Date: 19-Apr-21
Total Fleece Wt (lbs): 10.40

Laboratory Data

Mean Fiber Diameter: 23.5 microns
Standard Deviation: 5.1 microns
Coefficient of Variation: 21.5 %
Spin Fineness: 23.0 microns
Fibers Greater Than 30 microns: 8.6 %
Comfort Factor: 91.4 %

Mean Staple Length: 66 mm
Length Standard Deviation: 4.2 mm
Length Coefficient of Variation: 6.3 %
Mean Curvature: 53.9 deg/mm
SD Curvature: 23.9 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com