



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Dave Wiegman
PO BOX 1683, Flagstaff
AZ 86002-1683 US

Date: 19-Oct-22
Shear ID: 235956
Test No: 609063


Animal and Sample Description

Animal Name: Aza Azezite
Registry #: 35596448
Breed: Huacaya
Sex: Female
Colour: 100 - White

Date of Birth (Age): 29-May-18
Sample Location: GRID
Sample Date: 15-Apr-22
Previous Shear Date: 19-Apr-21
Total Fleece Wt (lbs): 5.70

Laboratory Data

Mean Fiber Diameter:	21.6 microns	Mean Staple Length:	94 mm
Standard Deviation:	4.6 microns	Length Standard Deviation:	9.5 mm
Coefficient of Variation:	21.2 %	Length Coefficient of Variation:	10.1 %
Spin Fineness:	21.0 microns	Mean Curvature:	49.9 deg/mm
Fibers Greater Than 30 microns:	3.0 %	SD Curvature:	21.1 deg/mm
Comfort Factor:	97.0 %	Medullated Fibers:	7.8 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com