



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

River Birch Farms
268B Tennessee Road, Winlock
WA 98596, US

Date: 20-Oct-22
Shear ID: 244153
Test No: 609565


Animal and Sample Description

Animal Name: Snr Greystones Peruvian Halo
Registry #: 32752953
Breed: Suri
Sex: Female
Colour: 301 - Medium Brown

Date of Birth (Age): 12-Mar-12
Sample Location: GRID
Sample Date: 3-Jun-22
Previous Shear Date:
Total Fleece Wt (lbs): 4.34

Laboratory Data

Mean Fiber Diameter:	29.0 microns	Mean Staple Length:	112 mm
Standard Deviation:	8.4 microns	Length Standard Deviation:	5.5 mm
Coefficient of Variation:	28.9 %	Length Coefficient of Variation:	4.9 %
Spin Fineness:	30.5 microns	Mean Curvature:	27.9 deg/mm
Fibers Greater Than 30 microns:	34.5 %	SD Curvature:	10.4 deg/mm
Comfort Factor:	65.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com