



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Stargazer Ranch
3800 Saulcy Ct, Loveland
CO 805

Date: 13-Oct-22
Shear ID:
Test No: 609089


Animal and Sample Description

Animal Name: Mayhem
Registry #:
Breed:
Sex:
Colour:

Date of Birth (Age):
Sample Location:
Sample Date: 15-May-22
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	18.4 microns	Comfort Factor:	99.5 %
Standard Deviation:	3.7 microns	Mean Curvature:	49.4 deg/mm
Coefficient of Variation:	20.3 %	SD Curvature:	38.2 deg/mm
Spin Fineness:	17.8 microns		
Fibers Greater Than 30 microns:	0.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com