



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Rhonda Deschner
PO Box 919, Wimberley
TX 78676, US

Date: 10-Jun-22
Shear ID: 230385
Test No: 607544

Animal and Sample Description


Animal Name: TP Val D Isere's Criterium
Registry #: 32547443
Breed: Huacaya
Sex: Male
Colour: 204 - Medium Fawn

Date of Birth (Age): 7-Jan-18
Sample Location: GRID
Sample Date: 10-Apr-22
Previous Shear Date: 3-Apr-21
Total Fleece Wt (lbs): 8.1

Laboratory Data

Mean Fiber Diameter: 19.9 microns
Standard Deviation: 4.1 microns
Coefficient of Variation: 20.6 %
Spin Fineness: 19.3 microns
Fibers Greater Than 30 microns: 2.1 %
Comfort Factor: 97.9 %

Mean Staple Length: 87 mm
Length Standard Deviation: 1.3 mm
Length Coefficient of Variation: 1.4 %
Mean Curvature: 57.4 deg/mm
SD Curvature: 25.6 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com