


WINDY'S INARA

AFD: 20.6 μ
SD: 4.6 μ
CV: 22.2 %
CF: 96.7 %
Curve: 45.5 Dg/mm
Min: 18.8 μ
Max: 22.6 μ
Staple: 100.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

WINDY'S INARA

AFD: 20.6 μ
SD: 4.6 μ
CV: 22.2 %
CF: 96.7 %
Curve: 45.5 Dg/mm
Min: 18.8 μ
Max: 22.6 μ
Staple: 100.0 mm

