


JAXON'S ARMANI

AFD: 22.5 μ
SD: 4.6 μ
CV: 20.3 %
CF: 93.9 %
Curve: 36.8 Dg/mm
Min: 21.4 μ
Max: 24.2 μ
Staple: 70.0 mm

% of Fibers



Alpaca Fiber Testing USA

JAXON'S ARMANI

AFD: 22.5 μ
SD: 4.6 μ
CV: 20.3 %
CF: 93.9 %
Curve: 36.8 Dg/mm
Min: 21.4 μ
Max: 24.2 μ
Staple: 70.0 mm

