


# B-JASMINE

**AFD:** 25.5  $\mu$   
**SD:** 5.4  $\mu$   
**CV:** 21.2 %  
**CF:** 83.2 %  
**Curve:** 33.3 Dg/mm  
**Min:** 25.0  $\mu$   
**Max:** 26.3  $\mu$   
**Staple:** 65.0 mm

% of Fibers



*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# B-JASMINE

**AFD:** 25.5  $\mu$   
**SD:** 5.4  $\mu$   
**CV:** 21.2 %  
**CF:** 83.2 %  
**Curve:** 33.3 Dg/mm  
**Min:** 25.0  $\mu$   
**Max:** 26.3  $\mu$   
**Staple:** 65.0 mm

