


CHERRY

AFD: 21.1 μ
SD: 4.6 μ
CV: 21.9 %
CF: 96.3 %
Curve: 16.4 Dg/mm
Min: 19.8 μ
Max: 22.9 μ
Staple: 0.0 mm

% of Fibers

Alpaca Fiber Testing USA



Fiber Diameter (microns)

CHERRY

AFD: 21.1 μ
SD: 4.6 μ
CV: 21.9 %
CF: 96.3 %
Curve: 16.4 Dg/mm
Min: 19.8 μ
Max: 22.9 μ
Staple: 0.0 mm

