


THYME

AFD: 24.8 μ
SD: 5.7 μ
CV: 23.1 %
CF: 84.3 %
Curve: 12.2 Dg/mm
Min: 23.0 μ
Max: 28.2 μ
Staple: 0.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

THYME

AFD: 24.8 μ
SD: 5.7 μ
CV: 23.1 %
CF: 84.3 %
Curve: 12.2 Dg/mm
Min: 23.0 μ
Max: 28.2 μ
Staple: 0.0 mm

