


BLACK DEW

AFD: 21.5 μ
SD: 4.8 μ
CV: 22.5 %
CF: 94.3 %
Curve: 16.0 Dg/mm
Min: 21.0 μ
Max: 23.8 μ
Staple: 115.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

BLACK DEW

AFD: 21.5 μ
SD: 4.8 μ
CV: 22.5 %
CF: 94.3 %
Curve: 16.0 Dg/mm
Min: 21.0 μ
Max: 23.8 μ
Staple: 115.0 mm

