


CHESCA'S ELECTRYONE

AFD: 23.0 μ
SD: 5.5 μ
CV: 23.9 %
CF: 90.0 %
Curve: 15.7 Dg/mm
Min: 22.9 μ
Max: 24.4 μ
Staple: 135.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

CHESCA'S ELECTRYONE

AFD: 23.0 μ
SD: 5.5 μ
CV: 23.9 %
CF: 90.0 %
Curve: 15.7 Dg/mm
Min: 22.9 μ
Max: 24.4 μ
Staple: 135.0 mm

