


RGAG PRINCE LEOPOLD

AFD: 22.2 μ
SD: 5.1 μ
CV: 23.0 %
CF: 92.5 %
Curve: 18.0 Dg/mm
Min: 20.6 μ
Max: 25.3 μ
Staple: 160.0 mm


% of Fibers



Fiber Diameter (microns)

RGAG PRINCE LEOPOLD

AFD: 22.2 μ
SD: 5.1 μ
CV: 23.0 %
CF: 92.5 %
Curve: 18.0 Dg/mm
Min: 20.6 μ
Max: 25.3 μ
Staple: 160.0 mm



Alpaca Fiber Testing USA