


# RGAF PRINCESS AURORA

**AFD:** 18.9  $\mu$   
**SD:** 4.7  $\mu$   
**CV:** 24.8 %  
**CF:** 98.0 %  
**Curve:** 18.1 Dg/mm  
**Min:** 18.1  $\mu$   
**Max:** 20.9  $\mu$   
**Staple:** 85.0 mm


% of Fibers



Fiber Diameter (microns)

# RGAF PRINCESS AURORA

**AFD:** 18.9  $\mu$   
**SD:** 4.7  $\mu$   
**CV:** 24.8 %  
**CF:** 98.0 %  
**Curve:** 18.1 Dg/mm  
**Min:** 18.1  $\mu$   
**Max:** 20.9  $\mu$   
**Staple:** 85.0 mm



*Alpaca Fiber Testing USA*