



Yocom-McColl Testing Laboratories, Inc.

540 West Elk Place • Denver, Colorado 80216-1823 USA

PHONE (303) 294-0582 • FAX (303) 295-6944

EMAIL: ymccoll@ymccoll.com

Optical Fiber Diameter Analyser (OFDA 100) Micron Test Report

Cedar Creek Alpacas/Angela & Alan Rogers
182 McNichols Rd
Cook WA 98605 USA

Date: 06/23/15

Test No: 903896


Animal and Sample Description

Animal Name: Cedar's Bugatti (2013)
Breed: Alpaca(Huacaya)
Sex: Male
Color: Beige


Animal ID: 32536249
Sample Location: Side
Sample Date: 06/06/13
Age: 06/08/12

Laboratory Data

Mean Fiber Diameter:	18.1 microns	Fibers Greater Than 30 microns:	0.6 %
Standard Deviation:	3.3 microns	Comfort Factor:	99.4 %
Coefficient of Variation:	18.5 %	Mean Curvature:	43.4 deg/mm
Spin Fineness:	17.2 microns	SD Curvature:	29.8 deg/mm



This Test Performed According to I.W.T.O Method 47



Yocom-McColl Testing Laboratories, Inc.

540 West Elk Place • Denver, Colorado 80216-1823 USA

PHONE (303) 294-0582 • FAX (303) 295-6944

EMAIL: ymccoll@ymccoll.com

Optical Fiber Diameter Analyser (OFDA 100) Micron Test Report

Cedar Creek Alpacas/Angela & Alan Rogers
182 McNichols Rd
Cook WA 98605 USA

Date: 06/23/15

Test No: 903897


Animal and Sample Description

Animal Name: Cedar's Bugatti (2014)
Breed: Alpaca(Huacaya)
Sex: Male
Color: Beige

Animal ID: 32536249
Sample Location: Side
Sample Date: 06/10/14
Age: 06/08/12

Laboratory Data

Mean Fiber Diameter:	17.2 microns	Fibers Greater Than 30 microns:	0.6 %
Standard Deviation:	3.7 microns	Comfort Factor:	99.4 %
Coefficient of Variation:	21.3 %	Mean Curvature:	52.6 deg/mm
Spin Fineness:	16.8 microns	SD Curvature:	28.3 deg/mm



This Test Performed According to I.W.T.O Method 47