


# HFAF ACCOYO SYDNEY

**AFD:** 20.8  $\mu$   
**SD:** 4.6  $\mu$   
**CV:** 22.1 %  
**CF:** 96.2 %  
**Curve:** 38.8 Dg/mm  
**Min:** 18.8  $\mu$   
**Max:** 23.7  $\mu$   
**Staple:** 100.0 mm

% of Fibers



*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# HFAF ACCOYO SYDNEY

**AFD:** 20.8  $\mu$   
**SD:** 4.6  $\mu$   
**CV:** 22.1 %  
**CF:** 96.2 %  
**Curve:** 38.8 Dg/mm  
**Min:** 18.8  $\mu$   
**Max:** 23.7  $\mu$   
**Staple:** 100.0 mm

