



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Blazing Star Ranch
2550 Windmill Circle, Elizabeth
CO 80107, US

Date: 21-Sep-23
Shear ID: 255027
Test No: 615412


Animal and Sample Description

Animal Name: Indie's Legacy of BSRA
Registry #: 35189589
Breed: Huacaya
Sex: Female
Colour: 360 - Bay Black

Date of Birth (Age): 21-Jul-21
Sample Location: GRID
Sample Date: 3-Jun-23
Previous Shear Date: 27-May-22
Total Fleece Wt (lbs): 7.05

Laboratory Data

Mean Fiber Diameter:	21.7 microns	Mean Staple Length:	108 mm
Standard Deviation:	4.8 microns	Length Standard Deviation:	3.1 mm
Coefficient of Variation:	22.0 %	Length Coefficient of Variation:	2.8 %
Spin Fineness:	21.3 microns	Mean Curvature:	49.8 deg/mm
Fibers Greater Than 30 microns:	3.8 %	SD Curvature:	27.7 deg/mm
Comfort Factor:	96.2 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com