


# SMILING MOON'S GREYSON

**AFD:** 22.0  $\mu$   
**SD:** 5.1  $\mu$   
**CV:** 23.4 %  
**CF:** 92.7 %  
**Curve:** 39.8 Dg/mm  
**Min:** 21.5  $\mu$   
**Max:** 23.6  $\mu$   
**Staple:** 90.0 mm

% of Fibers



Fiber Diameter (microns)

# SMILING MOON'S GREYSON

**AFD:** 22.0  $\mu$   
**SD:** 5.1  $\mu$   
**CV:** 23.4 %  
**CF:** 92.7 %  
**Curve:** 39.8 Dg/mm  
**Min:** 21.5  $\mu$   
**Max:** 23.6  $\mu$   
**Staple:** 90.0 mm

