


LOCK'S OF LUSTER'S NIKITA

AFD: 22.8 μ
SD: 5.3 μ
CV: 23.3 %
CF: 91.3 %
Curve: 13.5 Dg/mm
Min: 22.0 μ
Max: 26.4 μ
Staple: 125.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

LOCK'S OF LUSTER'S NIKITA

AFD: 22.8 μ
SD: 5.3 μ
CV: 23.3 %
CF: 91.3 %
Curve: 13.5 Dg/mm
Min: 22.0 μ
Max: 26.4 μ
Staple: 125.0 mm

