



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Bridgetown Suri Alpacas
9875 Bayside Rd Machipongo
VA 23405, US

Date: 15-Sep-21
Shear ID:
Test No: 604929


Animal and Sample Description

Animal Name: Bridgetown's Debonair by Jet
Registry #: 36074327
Breed:
Sex:
Colour: 410 - Dark Brown

Date of Birth (Age):
Sample Location: GRID
Sample Date: 25-Apr-21
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	19.0 microns	Mean Staple Length:	140 mm
Standard Deviation:	5.4 microns	Length Standard Deviation:	9.3 mm
Coefficient of Variation:	28.2 %	Length Coefficient of Variation:	6.6 %
Spin Fineness:	19.8 microns	Mean Curvature:	30.4 deg/mm
Fibers Greater Than 30 microns:	4.0 %	SD Curvature:	15.0 deg/mm
Comfort Factor:	96.0 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com