



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Bridgetown Suri Alpacas  
9875 Bayside Rd  
Machipongo, VA 23405-1833 US

Date: 17-Sep-20  
Shear ID: 205247  
Test No: 500472


### Animal and Sample Description

Animal Name: Bridgetown's Rocket by Jet  
Registry #: 36074273  
Breed: Suri  
Sex: Male  
Colour: 205 - Dark Fawn

Date of Birth (Age): 7-Jul-19  
Sample Location: GRID  
Sample Date: 26-Apr-20  
Previous Shear Date:  
Total Fleece Wt (lbs): 3.70

### Laboratory Data

Mean Fiber Diameter:	23.3 microns	Mean Staple Length:	167 mm
Standard Deviation:	4.7 microns	Length Standard Deviation:	12.1 mm
Coefficient of Variation:	20.4 %	Length Coefficient of Variation:	7.3 %
Spin Fineness:	22.5 microns	Mean Curvature:	9.7 deg/mm
Fibers Greater Than 30 microns:	7.0 %	SD Curvature:	11.9 deg/mm
Comfort Factor:	93.0 %	Medullated Fibers:	%



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Jude Davidson  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [nz.wool.timaru@sgs.com](mailto:nz.wool.timaru@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)