



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Bridgetown Suri Alpacas
9875 Bayside Rd Machipongo
VA 23405, US

Date: 15-Sep-21
Shear ID:
Test No: 604925


Animal and Sample Description

Animal Name: BTSA Poppy by Crown Prince Kodiak
Registry #: 36074280
Breed:
Sex:
Colour: 301 - Medium Brown

Date of Birth (Age):
Sample Location: GRID
Sample Date: 25-Apr-21
Previous Shear Date:
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter:	26.9 microns	Mean Staple Length:	186 mm
Standard Deviation:	7.7 microns	Length Standard Deviation:	7.3 mm
Coefficient of Variation:	28.7 %	Length Coefficient of Variation:	3.9 %
Spin Fineness:	28.2 microns	Mean Curvature:	28.6 deg/mm
Fibers Greater Than 30 microns:	26.5 %	SD Curvature:	11.7 deg/mm
Comfort Factor:	73.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com