



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Bridgetown Suri Alpacas
9875 Bayside Rd
Machipongo, VA 23405-1833 US

Date: 17-Sep-20
Shear ID: 205243
Test No: 500471


Animal and Sample Description

Animal Name: BRIDGETOWN'S VORNADO BY JET
Registry #: 35103738
Breed: Suri
Sex: Male
Colour: 202 - Light Fawn

Date of Birth (Age): 24-May-18
Sample Location: GRID
Sample Date: 26-Apr-20
Previous Shear Date: 19-Apr-19
Total Fleece Wt (lbs): 5.60

Laboratory Data

Mean Fiber Diameter:	19.5 microns	Mean Staple Length:	142 mm
Standard Deviation:	5.7 microns	Length Standard Deviation:	8.7 mm
Coefficient of Variation:	29.4 %	Length Coefficient of Variation:	6.1 %
Spin Fineness:	20.5 microns	Mean Curvature:	14.0 deg/mm
Fibers Greater Than 30 microns:	4.0 %	SD Curvature:	16.6 deg/mm
Comfort Factor:	96.0 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com