


# BERENGER

**AFD:** 25.5  $\mu$   
**SD:** 5.7  $\mu$   
**CV:** 22.5 %  
**CF:** 82.5 %  
**Curve:** 11.3 Dg/mm  
**Min:** 23.9  $\mu$   
**Max:** 27.9  $\mu$   
**Staple:** 115.0 mm

% of Fibers



*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# BERENGER

**AFD:** 25.5  $\mu$   
**SD:** 5.7  $\mu$   
**CV:** 22.5 %  
**CF:** 82.5 %  
**Curve:** 11.3 Dg/mm  
**Min:** 23.9  $\mu$   
**Max:** 27.9  $\mu$   
**Staple:** 115.0 mm



*Alpaca Fiber Testing USA*