


ELECTROFYRE'S LANSON

AFD: 21.4 μ
SD: 5.2 μ
CV: 24.0 %
CF: 95.2 %
Curve: 17.3 Dg/mm
Min: 17.9 μ
Max: 27.6 μ
Staple: 0.0 mm

% of Fibers


Alpaca Fiber Testing USA



Fiber Diameter (microns)

ELECTROFYRE'S LANSON

AFD: 21.4 μ
SD: 5.2 μ
CV: 24.0 %
CF: 95.2 %
Curve: 17.3 Dg/mm
Min: 17.9 μ
Max: 27.6 μ
Staple: 0.0 mm



Alpaca Fiber Testing USA