


RAYNAY'S ARGENT BY BERENGER

AFD: 20.3 μ
SD: 5.1 μ
CV: 25.1 %
CF: 95.2 %
Curve: 14.6 Dg/mm
Min: 17.8 μ
Max: 27.1 μ
Staple: 120.0 mm

% of Fibers

Alpaca Fiber Testing USA



Fiber Diameter (microns)

RAYNAY'S ARGENT BY BERENGER

AFD: 20.3 μ
SD: 5.1 μ
CV: 25.1 %
CF: 95.2 %
Curve: 14.6 Dg/mm
Min: 17.8 μ
Max: 27.1 μ
Staple: 120.0 mm

