


# RAYNAY'S CLARK SABLE

**AFD:** 21.6  $\mu$   
**SD:** 4.5  $\mu$   
**CV:** 20.9 %  
**CF:** 95.9 %  
**Curve:** 15.2 Dg/mm  
**Min:** 18.5  $\mu$   
**Max:** 24.2  $\mu$   
**Staple:** 0.0 mm

% of Fibers

*Alpaca Fiber Testing USA*



Fiber Diameter (microns)

# RAYNAY'S CLARK SABLE

**AFD:** 21.6  $\mu$   
**SD:** 4.5  $\mu$   
**CV:** 20.9 %  
**CF:** 95.9 %  
**Curve:** 15.2 Dg/mm  
**Min:** 18.5  $\mu$   
**Max:** 24.2  $\mu$   
**Staple:** 0.0 mm

