


AFD: 20.4 μ
SD: 4.5 μ
CV: 21.8 %
CF: 96.6 %
Curve: 35.8 Dg/mm
Min: 19.1 μ
Max: 21.7 μ
Staple: 100.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

KAISER

AFD: 20.4 μ
SD: 4.5 μ
CV: 21.8 %
CF: 96.6 %
Curve: 35.8 Dg/mm
Min: 19.1 μ
Max: 21.7 μ
Staple: 100.0 mm

