


# RAYNAY'S TEMPI BY PEYTON

**AFD:** 22.7  $\mu$   
**SD:** 5.3  $\mu$   
**CV:** 23.4 %  
**CF:** 91.1 %  
**Curve:** 16.1 Dg/mm  
**Min:** 21.5  $\mu$   
**Max:** 25.3  $\mu$   
**Staple:** 135.0 mm

% of Fibers




*Alpaca Fiber Testing USA*

Fiber Diameter (microns)

# RAYNAY'S TEMPI BY PEYTON

**AFD:** 22.7  $\mu$   
**SD:** 5.3  $\mu$   
**CV:** 23.4 %  
**CF:** 91.1 %  
**Curve:** 16.1 Dg/mm  
**Min:** 21.5  $\mu$   
**Max:** 25.3  $\mu$   
**Staple:** 135.0 mm



*Alpaca Fiber Testing USA*