



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sunny Alpacas
9200 Spooner Creek Ln Blaine
WA 98230 US

Date: 7-Jul-21
Shear ID: 221180
Test No: 602463

Animal and Sample Description


Animal Name: Sunny Accoyo Magma
Registry #: 35532293
Breed: Huacaya
Sex: Male
Colour: 100 - White

Date of Birth (Age): 25-Jul-20
Sample Location: GRID
Sample Date: 1-Jun-21
Previous Shear Date: 25-Jul-20
Total Fleece Wt (lbs): 3.71

Laboratory Data

Mean Fiber Diameter: 18.4 microns
Standard Deviation: 3.8 microns
Coefficient of Variation: 20.6 %
Spin Fineness: 17.9 microns
Fibers Greater Than 30 microns: 1.1 %
Comfort Factor: 98.9 %

Mean Staple Length: 105 mm
Length Standard Deviation: 6.1 mm
Length Coefficient of Variation: 5.8 %
Mean Curvature: 47.1 deg/mm
SD Curvature: 22.4 deg/mm
Medullated Fibers: 1.8 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com