


# RAYNAY'S PANTHA BY KARMA

**AFD:** 18.5  $\mu$   
**SD:** 4.2  $\mu$   
**CV:** 22.7 %  
**CF:** 98.9 %  
**Curve:** 17.8 Dg/mm  
**Min:** 16.9  $\mu$   
**Max:** 20.2  $\mu$   
**Staple:** 140.0 mm


% of Fibers



Fiber Diameter (microns)

# RAYNAY'S PANTHA BY KARMA

**AFD:** 18.5  $\mu$   
**SD:** 4.2  $\mu$   
**CV:** 22.7 %  
**CF:** 98.9 %  
**Curve:** 17.8 Dg/mm  
**Min:** 16.9  $\mu$   
**Max:** 20.2  $\mu$   
**Staple:** 140.0 mm



*Alpaca Fiber Testing USA*