



# Yocom-McColl Testing Laboratories, Inc.

540 West Elk Place • Denver, Colorado 80216-1823 USA

PHONE (303) 294-0582 • FAX (303) 295-6944

EMAIL: ymccoll@ymccoll.com

## Optical Fiber Diameter Analyser (OFDA 100) Micron Test Report

Akuna Matada Suris/Deb & Doug Christner  
28444 Redlands Mesa Rd  
Hotchkiss CO 81419-6210 USA

**Date:** 06/29/18  
**Shear ID:** 169115  
**Test No:** 962790


### Animal and Sample Description

**Animal Name:** Sweet Suri Petranella  
**ARI #:** 32516357  
**Breed:** Alpaca(Suri)  
**Sex:** Female  
**Color:** White

**Date of Birth (Age):** 10/26/12  
**Sample Location:** Side  
**Sample Date:** 05/25/18  
**Previous Shear Date:** 05/11/17  
**Total Fleece Wt (lbs):** 5.56

### Laboratory Data

<b>Mean Fiber Diameter:</b>	20.4 microns	<b>Mean Staple Length:</b>	134.4 mm
<b>Standard Deviation:</b>	4.7 microns	<b>Length Standard Deviation:</b>	3.9 mm
<b>Coefficient of Variation:</b>	22.8 %	<b>Length Coefficient of Variation:</b>	2.9 %
<b>Spin Fineness:</b>	20.2 microns	<b>Mean Curvature:</b>	10.9 deg/mm
<b>Fibers Greater Than 30 microns:</b>	2.6 %	<b>SD Curvature:</b>	11.0 deg/mm
<b>Comfort Factor:</b>	97.4 %	<b>Medullated Fibers:</b>	3.9 %



This Test Performed According to I.W.T.O Method 47