



Yocom-McColl Testing Laboratories, Inc.

540 West Elk Place • Denver, Colorado 80216-1823 USA

PHONE (303) 294-0582 • FAX (303) 295-6944

EMAIL: ymccoll@ymccoll.com

Optical Fiber Diameter Analyser (OFDA 100) Micron Test Report

Thordarson Farms/Heather Thordarson
13492 S. Warnock Rd
Oregon City OR 97045 USA

Date: 07/27/16

Test No: 927877


Animal and Sample Description

Animal Name: Winds of Posiedon's Storm
Breed: Alpaca(Huacaya)
Sex: Male
Color: Lt Fawn

Animal ID: 35234180
Sample Location: Side
Sample Date: 06/06/16
Age: 09/11/14

Laboratory Data

Mean Fiber Diameter:	22.2 microns	Fibers Greater Than 30 microns:	1.8 %
Standard Deviation:	3.7 microns	Comfort Factor:	98.2 %
Coefficient of Variation:	16.6 %	Mean Curvature:	43.9 deg/mm
Spin Fineness:	20.8 microns	SD Curvature:	23.1 deg/mm



This Test Performed According to I.W.T.O Method 47