



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Dean & Pamela Hiestand  
26417 Minkler Rd,  
Sedro Woolley, WA 98284 USA

Date: 25-Nov-20  
Shear ID:  
Test No: 501244


### Animal and Sample Description

Animal Name: Fiber Meadows Chantilly Lace  
Registry #: 35414520  
Breed: Huacaya  
Sex: Female  
Colour: Medium Fawn

Date of Birth (Age):  
Sample Location: GRID  
Sample Date:  
Previous Shear Date:  
Total Fleece Wt (lbs):

### Laboratory Data

Mean Fiber Diameter:	17.3 microns	Mean Staple Length:	70 mm
Standard Deviation:	3.6 microns	Length Standard Deviation:	3.7 mm
Coefficient of Variation:	20.6 %	Length Coefficient of Variation:	5.3 %
Spin Fineness:	16.8 microns	Mean Curvature:	61.8 deg/mm
Fibers Greater Than 30 microns:	0.5 %	SD Curvature:	33.7 deg/mm
Comfort Factor:	99.5 %	Medullated Fibers:	%



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Jude Davidson  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [nz.wool.timaru@sgs.com](mailto:nz.wool.timaru@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)