



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Timber Valley Ranch
724 Lewis Road, Royal Oaks
CA 95076, US

Date: 25-May-22
Shear ID: 230546
Test No: 606661


Animal and Sample Description

Animal Name: Tvalley Velvet Valentino
Registry #: 35385721
Breed: Huacaya
Sex: Male
Colour: 500 - True Black

Date of Birth (Age): 27-May-20
Sample Location: GRID
Sample Date: 18-Apr-22
Previous Shear Date: 25-Mar-21
Total Fleece Wt (lbs): 7.18

Laboratory Data

Mean Fiber Diameter:	22.7 microns	Mean Staple Length:	112 mm
Standard Deviation:	5.1 microns	Length Standard Deviation:	3.3 mm
Coefficient of Variation:	22.2 %	Length Coefficient of Variation:	2.9 %
Spin Fineness:	22.4 microns	Mean Curvature:	42.5 deg/mm
Fibers Greater Than 30 microns:	7.4 %	SD Curvature:	16.5 deg/mm
Comfort Factor:	92.6 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com