

Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

en Seven Acre 07 Galchutt Av ND 58075-8101	ve, Galchutt		Date: Shear ID: Test No:	11-Aug-21 220628 603863	
		Animal and S	ample Description		
Animal Name: Registry #: Breed: Sex: Colour:	Ten Seven Acres' I Am Batman 35599470 Huacaya Male 360 - Bay Black		Date of Birth (Age): Sample Location: Sample Date: Previous Shear Date: Total Fleece Wt (lbs):	20-Sep-19 GRID 7-May-21 6-May-20 4.27	
		Labor	ratory Data		
Mean Fiber Diameter: Standard Deviation: Coefficient of Variation: Spin Fineness: Fibers Greater Than 30 microns: Comfort Factor:		19.8 microns 3.8 microns 19.1 % 18.9 microns 1.3 % 98.7 %	Mean Staple Length: Length Standard Deviation: Length Coefficient of Variation: Mean Curvature: SD Curvature:		88 mm 5.4 mm 6.2 % 45.1 deg/mm 17.7 deg/mm
14%					
12% —— 10% ——					
Percent of Observations %9 %8					
ercent of (%					
4%					
2% ——			h.		
0% — 0	 _ 		30 35 40 r Diameter - Microns	45 50	55 60

Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear Business Manager

loasa Kosena Authorised Signatory

SGS General Terms and Conditions

The validity of this document may be confirmed by contacting the address shown below SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: <u>WoolOnline@sgs.com</u> Web: <u>www.wooltesting.sgs.com</u>